



terrazzo tiles

kingsstone

Terrazzo

- cement-Base terrazzo
- recomposed stone
- ingredients : marble aggregate
Portland cement
water

Tiles


Standard Sizes (panel size / thickness)

30 x 30 / 2cm	50 x 30 / 2cm	60 x 30 / 2cm
40 x 40 / 2cm	60 x 40 / 2cm	60 x 60 / 2cm

other sizes can be produced on request

Finishes

- Honed
- Polished
- Brushed
- Bush Hammered



color and structure of the listed items in this catalog are only for indication. As the products consist natural material which are subject to color and structure alternation.

Application

- Indoor and outdoor Flooring
- indoor and outdoor Cladding

ksm 371.100



Flexural Strength

$\geq 9,40$ Mpa

Water Absorption

$\leq 4,11$ M%

Resistance to abrasion


$\leq 19,80$ cm³/50cm²

Resistance to compression

≥ 60 Mpa

Slippage Resistance

Standard R9



ksm 522.102



Flexural Strength

$\geq 9,70$ Mpa

Water Absorption

$\leq 3,99$ M%

Resistance to abrasion


$\leq 20,10$ cm³/50cm²

Resistance to compression

≥ 60 Mpa

Slippage Resistance

Standard R9



ksm 523.103



Flexural Strength

≥ 9,50 Mpa

Water Absorption

≤ 3,61 M%

Resistance to abrasion

≤ 19,40 cm³/50cm²

Resistance to compression

≥ 60 Mpa

Slippage Resistance

Standard R9



ksm 525.104



Flexural Strength

$\geq 11,20$ Mpa

Water Absorption

$\leq 3,63$ M%

Resistance to abrasion

≤ 17 cm³/50cm²

Resistance to compression

≥ 60 Mpa

Slippage Resistance

Standard R9



ksm 526.105



Flexural Strength

$\geq 9,10$ Mpa

Water Absorption

$\leq 4,60$ M%

Resistance to abrasion

$\leq 17,80$ cm³/50cm²

Resistance to compression


≥ 60 Mpa

Slippage Resistance

Standard R9



HONED



POLISHED



BRUSHED



**BUSH
HAMMERED**

ksm 527.106



Flexural Strength

$\geq 10,10 \text{ Mpa}$

Water Absorption

$\leq 3,47 \text{ M\%}$

Resistance to abrasion


$\leq 16 \text{ cm}^3/50\text{cm}^2$

Resistance to compression


$\geq 60 \text{ Mpa}$

Slippage Resistance

Standard R9



ksm 528.109



Flexural Strength

$\geq 9,30$ Mpa

Water Absorption

$\leq 3,11$ M%

Resistance to abrasion

$\leq 21,00$ cm³/50cm²

Resistance to compression

≥ 60 Mpa

Slippage Resistance

Standard R9



HONED



POLISHED




BRUSHED



**BUSH
HAMMERED**

ksm 529.111



Flexural Strength

$\geq 8,50$ Mpa

Water Absorption

$\leq 5,40$ M%

Resistance to abrasion

$\leq 15,20$ cm³/50cm²

Resistance to compression


≥ 60 Mpa

Slippage Resistance

Standard R9



HONED



POLISHED



BRUSHED



**BUSH
HAMMERED**

ksm 518.124



Flexural Strength

≥ 10,40 Mpa

Water Absorption

≤ 2,20 M%

Resistance to abrasion

≤ 19,10 cm³/50cm²

Resistance to compression

≥ 60 Mpa

Slippage Resistance

Standard R9



ksm 370.130



Flexural Strength

$\geq 9,90$ Mpa

Water Absorption

$\leq 4,30$ M%

Resistance to abrasion

$\leq 21,90$ cm³/50cm²

Resistance to compression

≥ 60 Mpa

Slippage Resistance

Standard R9



ksm 371.135



Flexural Strength

≥ 10,20 Mpa

Water Absorption

≤ 2,20 M%

Resistance to abrasion

≤ 19,90 cm³/50cm²

Resistance to compression


≥ 60 Mpa

Slippage Resistance

Standard R9



ksm 372.136



Flexural Strength

≥ 11,50 Mpa

Water Absorption

≤ 2,36 M%

Resistance to abrasion

≤ 23,00 cm³/50cm²

Resistance to compression

≥ 60 Mpa

Slippage Resistance

Standard R9



ksm 372.137



Flexural Strength

≥ 9,90 Mpa

Water Absorption

≤ 3,86 M%

Resistance to abrasion

≤ 16,50 cm³/50cm²

Resistance to compression

≥ 60 Mpa

Slippage Resistance

Standard R9



ksm 372.138



Flexural Strength

≥ 10,50 Mpa

Water Absorption

≤ 4,19 M%

Resistance to abrasion

≤ 19,80 cm³/50cm²

Resistance to compression

≥ 60 Mpa

Slippage Resistance

Standard R9



ksm 373.139



Flexural Strength

$\geq 8,20$ Mpa

Water Absorption

$\leq 3,44$ M%

Resistance to abrasion


$\leq 19,20$ cm³/50cm²

Resistance to compression

≥ 60 Mpa

Slippage Resistance

Standard R9



ksm 375.041



Flexural Strength

$\geq 9,40$ Mpa

Water Absorption

$\leq 4,11$ M%

Resistance to abrasion

$\leq 19,80$ cm³/50cm²

Resistance to compression

≥ 60 Mpa

Slippage Resistance

Standard R9



ksm 372.143



Flexural Strength

$\geq 8,10$ Mpa

Water Absorption

$\leq 2,70$ M%

Resistance to abrasion


$\leq 19,60$ cm³/50cm²

Resistance to compression

≥ 60 Mpa

Slippage Resistance

Standard R9



ksm 376.147



Flexural Strength

$\geq 8,40$ Mpa

Water Absorption

$\leq 5,98$ M%

Resistance to abrasion

$\leq 16,70$ cm³/50cm²

Resistance to compression

≥ 60 Mpa

Slippage Resistance

Standard R9



ksm 377.148



Flexural Strength

$\geq 9,80$ Mpa

Water Absorption

$\leq 5,19$ M%

Resistance to abrasion

$\leq 17,20$ cm³/50cm²

Resistance to compression

≥ 60 Mpa

Slippage Resistance

Standard R9



ksm 525.149



Flexural Strength

$\geq 10,00$ Mpa

Water Absorption

$\leq 4,00$ M%

Resistance to abrasion


$\leq 18,00$ cm³/50cm²

Resistance to compression

≥ 60 Mpa

Slippage Resistance

Standard R9



ksm 525.151



Flexural Strength

≥ 10,50 Mpa

Water Absorption

≤ 4,92 M%

Resistance to abrasion

≤ 17,10 cm³/50cm²

Resistance to compression

≥ 60 Mpa

Slippage Resistance

Standard R9

HONED

POLISHED

BRUSHED

**BUSH
HAMMERED**

ksm 526.153



Flexural Strength

$\geq 9,70$ Mpa

Water Absorption

$\leq 3,68$ M%

Resistance to abrasion


$\leq 15,80$ cm³/50cm²

Resistance to compression

≥ 60 Mpa

Slippage Resistance

Standard R9



ksm 527.159



Flexural Strength

$\geq 9,40$ Mpa

Water Absorption

$\leq 3,45$ M%

Resistance to abrasion

$\leq 21,00$ cm³/50cm²

Resistance to compression

≥ 60 Mpa

Slippage Resistance

Standard R9



HONED



POLISHED




BRUSHED



**BUSH
HAMMERED**

ksm 528.160



Flexural Strength

$\geq 8,00$ Mpa

Water Absorption

$\leq 3,37$ M%

Resistance to abrasion


$\leq 19,10$ cm³/50cm²

Resistance to compression

≥ 60 Mpa

Slippage Resistance

Standard R9



ksm 698.173



Flexural Strength

≥ 8,90 Mpa

Water Absorption

≤ 2,55 M%

Resistance to abrasion

≤ 19,80 cm³/50cm²

Resistance to compression


≥ 60 Mpa

Slippage Resistance

Standard R9



ksm 529.175



Flexural Strength

$\geq 10,60$ Mpa

Water Absorption

$\leq 3,42$ M%

Resistance to abrasion


$\leq 18,80$ cm³/50cm²

Resistance to compression

≥ 60 Mpa

Slippage Resistance

Standard R9



ksm 530.177



Flexural Strength

$\geq 9,90$ Mpa

Water Absorption

$\leq 2,66$ M%

Resistance to abrasion

$\leq 13,90$ cm³/50cm²

Resistance to compression

≥ 60 Mpa

Slippage Resistance


Standard R9



HONED



POLISHED



BRUSHED



**BUSH
HAMMERED**

ksm 371.178



Flexural Strength

$\geq 9,10$ Mpa

Water Absorption

$\leq 3,37$ M%

Resistance to abrasion


$\leq 19,10$ cm³/50cm²

Resistance to compression


≥ 60 Mpa

Slippage Resistance

Standard R9



ksm 698.210



Flexural Strength

$\geq 9,40$ Mpa

Water Absorption

$\leq 4,11$ M%

Resistance to abrasion

$\leq 19,80$ cm³/50cm²

Resistance to compression

≥ 60 Mpa

Slippage Resistance

Standard R9



ksm 696.220



Flexural Strength

$\geq 9,00$ Mpa

Water Absorption

$\leq 3,44$ M%

Resistance to abrasion


$\leq 14,50$ cm³/50cm²

Resistance to compression


≥ 60 Mpa

Slippage Resistance

Standard R9



ksm 697.230



Flexural Strength

$\geq 9,40$ Mpa

Water Absorption

$\leq 4,11$ M%

Resistance to abrasion


$\leq 19,80$ cm³/50cm²

Resistance to compression


≥ 60 Mpa

Slippage Resistance

Standard R9



ksm 525.240



Flexural Strength

$\geq 9,10$ Mpa

Water Absorption

$\leq 3,37$ M%

Resistance to abrasion

$\leq 19,10$ cm³/50cm²

Resistance to compression

≥ 60 Mpa

Slippage Resistance

Standard R9



ksm 372.250



Flexural Strength

$\geq 8,10$ Mpa

Water Absorption

$\leq 2,70$ M%

Resistance to abrasion


$\leq 19,60$ cm³/50cm²

Resistance to compression

≥ 60 Mpa

Slippage Resistance

Standard R9



ksm 373.290



Flexural Strength

≥ 8,00 Mpa

Water Absorption

≤ 4,00 M%

Resistance to abrasion

≤ 20,00 cm³/50cm²

Resistance to compression

≥ 60 Mpa

Slippage Resistance


Standard R9



HONED



POLISHED



BRUSHED



**BUSH
HAMMERED**

kingsstone

e.: kstone@kingsholdings.com

t.: +852 3597 9309